

SECTION 216 – STREET MARKING PAINT

1. GENERAL

This work shall be performed in accordance with section 807 of the latest version of the KDOT Standard Specifications and as amended herein.

2. MATERIALS

The traffic paint and glass beads used shall meet all requirements from section 2215 of the latest version of the KDOT Standard Specifications.

3. SURFACE PREPARATION

No pavement markings should be applied to any surface that is not clean and dry. If necessary the contractor may need to clean and prep any surface before applying the pavement markings at the Contractor's expense.

4. PAINT

Paint shall be applied at the rate specified by the manufacturer to achieve a minimum of 18 mils for the wet film thickness.

5. GLASS BEADS

Glass beads shall be applied at a minimum rate of 10 pounds of beads for each gallon of paint.

6. MEASUREMENT OF PAYMENT

Payment for this work shall be made at the contract linear foot price for each color and width specified in the contract documents, which price shall be full compensation for all materials, labor, equipment and incidentals necessary to complete the work.